# PTFE+25%Glass - teflon glass filled

Other material names PTFE+25%Glass: Murflor+glasfiber

Material group: Teflon

Glass filled PTFE is used to improve the creep resistance of PTFE over all temperature ranges, while still allowing some compression required for sealing in both gaskets and valves. Improved wear behavior is exhibited, while there is little effect on the electrical properties, as glass fiber is an insulator. Glass has an exceptional resistance to water. Glass must be avoided with the use of strong alkalis and hydrofluoric acid.



### Color of material:



## **Typical applications:**

- ideal for high load bearing applications, against high hardness surfaces.
- bearings and bearing pads
- piston rings,
- valve seats and valve plugs
- gaskets







### The material is used in:

Electrotechnical industry Automobile industry Chemical industry **Engineering industry** Paper industry Glass industry

Production of single-purpose machines


### **Features:**

- Chemically inert to all known industrial chemicals;
- Low co-efficient of friction, non-stick & non-toxic;
- Wide temperature range
- Exhibits excellent permeation resistance;
- Excellent dielectric properties;

Material availability: Production only on request

Material properties table

Specific weight 2.24 g/cm<sup>3</sup> Tensile strength 19 N/mm<sup>2</sup> Allowable mean pressure deformation 1% 8.20 N/mm<sup>2</sup> p.v dry limit 0.18 MPa.m/s



Flexural strength 4 N/mm<sup>2</sup> 250 % **Tensibility** Flexural modulus 1 320 N/mm<sup>2</sup> Tensile modulus 1 500 N/mm<sup>2</sup> **Impact toughness** bez zlomu **Notched toughness**  $>12 \text{ kJ/m}^2$ 65 N/mm<sup>2</sup> **Ball hardness Friction coefficient** 0.13 1.30 um/km Sliding wear **Antistatic material** No **Electrical strength** 13 kV/mm  $10^{(16)} \Omega$ Specific internal resistance Specific surface resistance 10 $^(16)$  Ω.cm **Melting point** 327 °C Thermal expansion 12 10^(-5)/K Thermal conductivity 0.90 W/(K.m)Permanent use temperature -200; 260 °C -200; 280 °C Transient temperature of use Absorbability 0,01 % Water absorption 0,01 % **Resistance - oils** resistant Acid resistance resistant **Durability - alcali** resistant **Food contact** No

Engineering plastics are supplied in the form of bars, plates, strips, tubes and sheets. From the semi-finished products the company TechPlasty has regularly in stock, we also supply blanks.

All standard and special materials are designed to meet your specific requirements. Their mechanical, thermal, and electrical properties and chemical resistance satisfy the most demanding requirements and this allows them to work even in the most difficult conditions. If you need advice when choosing the appropriate material for your application, please contact us. We'll gladly advise you. You can utilize the long-term experience of our technical advisors free-of- charge, who can visit you right in your operation and solve your requirements for engineering plastics directly at the site of their usage.

**TechPlasty, s.r.o.** Kysucká 7/A 010 01 Žilina Slovakia

